

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
8 April 2004 (08.04.2004)

PCT

(10) International Publication Number
WO 2004/029342 A1

- (51) International Patent Classification⁷: **D01F 6/46**, (74) Agent: **FISAULI, Beatrice**; Basell Poliolefine Italia S.p.A, Intellectual Property, Via Pergolesi 25, I-20124 Milano (IT).
- (21) International Application Number: **PCT/EP2003/010707**
- (22) International Filing Date: **23 September 2003 (23.09.2003)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
02021421.9 25 September 2002 (25.09.2002) EP
60/416,992 8 October 2002 (08.10.2002) US
- (71) Applicant (for all designated States except US): **BASELL POLIOLEFINE ITALIA S.P.A.** [IT/IT]; Via Pergolesi 25, I-20124 Milano (IT).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **SARTORI, Franco** [IT/IT]; Via A. M. Mozzoni, 1, I-44100 Ferrara (IT). **LONARDO, Angelo** [IT/IT]; Via Pacuvio 33, I-80122 Napoli (IT). **HERBEN, Pierre** [BE/BE]; Rue A. Delporte 44, B-1050 Bruxelles (BE).
- (81) Designated States (national): AU, BR, CA, CN, CO, CZ, HU, ID, IL, IN, JP, KR, MX, NO, PH, PL, RO, RU, SG, SK, UA, US, YU, ZA.
- (84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).
- Declarations under Rule 4.17:**
- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
 - of inventorship (Rule 4.17(iv)) for US only
- Published:**
- with international search report
 - before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **POLYPROPYLENE FIBRES SUITABLE FOR SPUNBONDED NON-WOVEN FABRICS**

(57) Abstract: A fibre for spunbonded fabrics comprising a propylene polymer composition (A) having an MFR (1) value from 6 to 150 g/10 min and being selected from (i) a crystalline propylene random copolymer or crystalline propylene polymer composition containing at least 0.8% by weight of ethylene and having a melting temperature of 153° C or higher, a content of fraction soluble in xylene at room temperature lower than 10% by weight, and a value of the ratio of the polymer fraction collected at the temperature range from 25° to 95° C to the xylene soluble fraction at room temperature higher than 4; and (ii) a crystalline propylene polymer composition having a melting temperature of 153° C or higher, a content of fraction soluble in xylene at room temperature lower than 10% by weight; the said composition containing at least 0.64 wt% of ethylene or a C₄-C₁₀ α-olefin recurring unit and comprising: (1) 20-80 wt% of a crystalline propylene polymer containing up to 1.5 wt% of ethylene and/or C₄-C₁₀ α-olefin; and (II) 20-80 wt% of a crystalline propylene random copolymer selected from (IIa) a copolymer of propylene with 0.8 to 10 wt% of ethylene and/or (IIb) a copolymer of propylene with 1.5 to 18 wt% of a C₄-C₁₀ α-olefin. Said polymer composition (A) is obtainable by way of chemical degradation of a precursor polymer composition (A) having MFR values (MFR (2)) of from 0.5 to 50 g/10 min, provided that the ratio of MFR (1) to MFR (2) be from 1.5 to 60. Propylene polymer composition (ii) as described above and non-woven fabrics that are prepared with the said fibres. The said fabric is useful for coverstock and diapers.

WO 2004/029342 A1